



Brushable Ceramic White

Description: A brushable, high-performance, ceramic-filled epoxy for sealing, protecting, and repairing surfaces subject to erosion, corrosion, and wear

Intended Use: Protect pump casings, impeller blades, gate valves, water boxes, and fan blades; rebuild heat exchangers, tube sheets, and other water circulating equipment; top coat on repaired surfaces; seal and protect new equipment exposed to erosion and corrosion

Product features:

- Excellent chemical resistance
- Temperature resistance to 350°F
- Applies easily with short-bristle brush or roller
- Low viscosity, self-leveling liquid
- Acceptable for use in meat and poultry plants
- NSF® Approved (Certified to ANSI/NSF61)

Limitations: None

Typical Physical Properties: *Technical data should be considered representative or typical only and should not be used for specification purposes.*

Cured 7 days @ 75° F

Color	White
Mix Ratio by Volume	5.6:1
Mix Ratio by Weight	8.5:1
% Solids by Volume	100
Pot Life @ 75F	21 min.
Specific Volume	16.5 in.(3)/lb.
Cured Shrinkage	0.0020 in./in.
Specific Gravity	1.53 gm/cc
Temperature Resistance	Wet 150°F
Coverage/lb	7.6 sq.ft./lb. @ 15 mils(.015 in.)
Cured Hardness	87D
Dielectric Strength	382 volts/mils
Dielectric Constant	38.7
Adhesive Tensile Shear	2,000 psi
Compressive Strength	15,200 psi
Modulus of Elasticity	9.0 psi x 10(5) in.
Flexural Strength	8,000 psi
Coefficient of Thermal Expansion	19 [(in.) x (in.) x °F] x 10(-6)
Thermal Conductivity	1.92 [(cal x cm) / (sec x cm(2) x °C)] x 10(-3)
Brush Coat Thickness	10-20 mils (.010 - .020 in.)
Cure Time	16 hrs.
Recoat Time	4-6 hrs.
Salt Spray Resistance	5,000 hrs.
Mixed Viscosity	40,000 cps

TESTS CONDUCTED

Coef. of Thermal Expansion ASTM D 696
Cure Shrinkage ASTM D 2566
Dielectric Strength, volts/mil ASTM D 149
Modulus of Elasticity ASTM D 638
Cured Hardness Shore D ASTM D 2240
Adhesive Tensile Shear ASTM D 1002
Compressive Strength ASTM D 695
Dielectric Constant ASTM D 150
Flexural Strength ASTM D 790
Thermal Conductivity ASTM C 177

Surface Preparation:

1. Thoroughly clean the surface with Devcon® Cleaner Blend 300 to remove all oil, grease, and dirt.
2. Grit blast surface area with 8-40 mesh grit, or grind with a coarse wheel or abrasive disc pad, to create increased surface area for better adhesion (Caution: An abrasive disc pad can only be used provided white mesh is revealed). Desired profile is 3-5mil, including defined edges (do not "feather-edge" epoxy).

Note: For metals exposed to sea water or other salt solution, grit-blast and high-pressure-water-blast the area, then leave overnight to allow any salts in the metal to "sweat" to the surface. Repeat blasting to "sweat out" all soluble salts. Perform chloride contamination test to determine soluble salt content (should be no more than 40ppm).

3. Clean surface again with Cleaner Blend 300 to remove all traces of oil, grease, dust, or other foreign substances from the grit blasting.

4. Repair surface as soon as possible to eliminate any changes or surface contaminants.

WORKING CONDITIONS: Ideal application temperature is 55°F to 90°F. In cold working conditions, heat repair area to 100-110°F immediately prior to applying epoxy to dry off any moisture, contamination, or solvents, as well as to assist epoxy in achieving maximum adhesion properties.

Mixing Instructions:

---- It is strongly recommended that full units be mixed, as ratios are pre-measured. ----

1. Add hardener to resin
2. Mix thoroughly with screwdriver or similar tool (continuously scrape material away from sides and bottom of container) until a uniform, streak-free consistency is obtained.

LARGE SIZES (2 lb., 25 lb.): Use a propeller-type Jiffy Mixer Model ES on an electric drill. Mix until color is uniform and consistent.

Note: Keep propeller below liquid line, as additional air can be added to mixture, resulting in air bubbles on the surface of the finished product.

Application Instructions:

Apply two thin coats (8-15 mils) of Brushable Ceramic to ensure a lack of pinholes or holidays on the substrate (a low voltage, holiday detector will ensure a pinhole-free coating). Brushable Ceramic fully cures in 16 hours, at which time it can be machined, drilled or painted.

FOR GREATER THICKNESS

Use Brushable Ceramic as a coating in combination with Ceramic Repair Putty. For proper wear and adhesion, maximum thickness should not exceed 40 mils.

FOR ± 70°F APPLICATIONS

Applying epoxy at temperatures below 70°F lengthens functional cure and pot life times. Conversely, applying above 70°F shortens functional cure and pot life.

Storage:

Store at room temperature.

Compliances:

NSF-certified for potable water applications
Approved for use in meat and poultry processing plants

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F

Benzene	Excellent	Sodium Hydroxide 10%	Excellent
Gasoline (Unleaded)	Excellent	Sodium Hydroxide 50%	Excellent
Hydrochloric 10%	Very good	Sodium Hypochlorite	Very good
Kerosene	Excellent	Sulfuric 10%	Very good
Mineral Spirits	Excellent	Sulfuric 50%	Fair
Nitric 50%	Poor	Toluene	Excellent
Phosphoric 10%	Very good	Xylene	Fair
Potassium Hydroxide 40%	Excellent		

Precautions:

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-800-933-8266

FOR INDUSTRIAL USE ONLY

Warranty:

Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

Order Information:

11770 2 lb.