



## Customer Specification Dura-Touch SS 34-175

### A. GENERAL DESCRIPTION

- ◆ Disposable, ambidextrous, powder-free, white, soft stretch vinyl glove.  
(Note: Contains **no** natural rubber latex)

### B. OUTSTANDING CHARACTERISTICS

- ◆ Provides the comfort, dexterity and tactile sensitivity of latex without the risk of latex allergies.

### C. APPLICATIONS

- ◆ Food processing & handling
- ◆ Small parts handling
- ◆ Maintenance & cleanup
- ◆ Janitorial use

### D. DIMENSIONAL PARAMETERS

LOCATION	SMALL	MEDIUM	LARGE	XLARGE	TEST METHOD
Palm Width (mm)	85 $\pm$ 5	95 $\pm$ 5	105 $\pm$ 5	115 $\pm$ 5	ASTM D 5250/ASTM D 3767
Thumb Length (mm)	50 $\pm$ 2	52 $\pm$ 2	56 $\pm$ 2	62 $\pm$ 2	
Index Finger Length (mm)	60 $\pm$ 2	68 $\pm$ 2	75 $\pm$ 2	84 $\pm$ 2	
Middle Finger Length (mm)	74 $\pm$ 2	80 $\pm$ 2	86 $\pm$ 2	95 $\pm$ 2	
Ring Finger Length (mm)	66 $\pm$ 2	73 $\pm$ 2	80 $\pm$ 2	88 $\pm$ 2	
Little Finger Length (mm)	49 $\pm$ 2	54 $\pm$ 2	56 $\pm$ 2	64 $\pm$ 2	
Total Length (mm)	240 Min	240 Min	240 Min	240 Min	ASTM D 5250/ASTM D 3767

### E. PHYSICAL PROPERTIES

PROPERTY	TOLERANCE	TEST METHOD
Thickness: Palm – mm ( <i>mils</i> )	0.07 mm ( <i>2.8 mils</i> ) Minimum	ASTM D 5250/ASTM D 3767
Thickness: Cuff – mm ( <i>mils</i> )	0.11 mm ( <i>4.7 mils</i> ) Minimum	ASTM D 5250/ASTM D 3767
Thickness: Finger – mm ( <i>mils</i> )	0.12 mm ( <i>4.7 mils</i> ) Minimum	ASTM D 5250/ASTM D 3767
Weight (g/piece – Minimum)	(S) – 6.0; (M) – 6.5; (L) – 7.0; (XL) – 7.5	
Tensile Strength: psi ( <i>Mpa</i> )	1595 psi ( <i>11 Mpa</i> ) Minimum	ASTM D 3578/ASTM D 412
Ultimate Elongation: (%)	380 Minimum	ASTM D 3578/ASTM D 412
Pin Holes/Water Tightness	1.5 AQL	ASTM D 5250/ASTM D 5151

### F. OTHER CHARACTERISTICS

- ◆ All components comply with FDA food handling regulation 21 CFR 177.2600.
- ◆ Complies with ASTM D 5250 Standard Specification for Poly Vinyl Chloride Gloves in Medical Application.
- ◆ Contains no silicone-based materials in formulation or processing adjuvants.

### G. PACKAGING PROTOCOL

- ◆ 10 dispensers at 100 each per case (or 1000 each per case)

NEITHER THIS NOR ANY STATEMENT MADE BY OR ON BEHALF OF ANSELL HEREIN IS A WARRANTY THAT ANY PRODUCT IS FIT FOR A PARTICULAR PURPOSE, AND ANSELL SHALL NOT BE LIABLE TO ANYONE WITH RESPECT TO THIS INFORMATION.

*This document is the property of Ansell and the information contained herein is proprietary to Ansell.*