



Features

- Partitions are adjustable for different size parts
- Impregnated corrugated material; greater durability than coated or printed material
- Static dissipative surface resistance of 1×10^6 to $< 1 \times 10^9$ ohms per ANSI/ESD STM11.11
- Made from 100% recycled material, and is 100% recyclable
- Reusable, ensuring best value
- For cell configurations click [here](#)

Meets the required limits of ANSI/ESD S20.20, and Packaging standard ANSI/ESD S541.

SPECIFICATIONS

Properties

Surface Resistance

Discharge Shielding

Sloughing Test

Recyclability

Typical Values

1×10^6 to $< 1 \times 10^9$ ohms

< 50 nanoJoules

Negligible surface damage at 10 cycles and $< 5\%$ of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Test Procedures/Method

ANSI/ESD STM11.11

ANSI/ESD STM 11.31

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992



Made in the
United States of America

Specifications and procedures subject to change without notice.

Tolerances are +/- 10% unless otherwise specified

TEK-TRAY PARTITION SET

PROTEKTIVE PAK

PROTEKTIVE PAK

13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578, FAX (909) 363-7331

ProtektivePak.com

DRAWING NUMBER
37764

DATE:
March
2016